



CATEGORY:



CLEARED

ADDRESS
CONTACT IF FOUND:

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE
REQUEST FOR FILING APPLICATION UNDER RULE 53(b)**

Pursuant to 37 CFR 1.53(b), please file a ☐ continuation/☒ divisional
of the pending prior PATENT APPLICATION U.S. PTO
Inventor: Brodeur et al
Serial No. 09/063,377
Filed: April 21, 1998
For: **REINFORCED FOAM BACKED CARPET**
Assistant Commissioner for Patents
Washington, DC 20231
Sir:

Atty Dkt.: 11-895
C# M#
Date: August 16, 2000
Group: 1733
Examiner: Yao



This request for filing under Rule 53(b) is made by the following named inventor(s) (using the above-identified title):
Inventor(s): Brodeur et al

- ☒ Attached is a true copy of the prior application as originally filed including the specification, claims, Oath/Declaration and drawings (if any) and abstract (if any). No amendments (if any) referenced in the Oath or Declaration filed to complete the prior application introduced new matter.
- ☐ Priority is hereby claimed under 35 USC 119 based on the following foreign applications, the entire content of which is hereby incorporated by reference in this application:

<u>Application Number</u>	<u>Country</u>	<u>Day/Month/Year/Filed</u>
---------------------------	----------------	-----------------------------

☐ certified copy(ies) of foreign application(s) attached or

☐ already filed on _____ in prior appln. no. _____ filed _____

☐ already filed in _____ filed _____

- ☐ Please amend the specification by inserting before the first line: -- This application claims the benefit of U.S. Provisional Application No. _____, filed _____, the entire content of which is hereby incorporated by reference in this application.--

☒ The prior application is assigned to Burlington Industries, Inc..

☒ Power of Attorney has been granted to Robert A. Vanderhye et al, Reg. No. 27,076 of Nixon & Vanderhye P.C., 1100 N. Glebe Rd., 8th Flr, Arlington, VA 22201.

☒ Address all future communications to: Nixon & Vanderhye P.C., 1100 N. Glebe Rd., 8th Floor, Arlington, VA 22201.

☒ Please amend the specification by inserting before the first line --This is a divisional of application Serial No. 09/063,377, filed April 21, 1998, now pending, the entire content of which is hereby incorporated by reference in this application.--

☒ ALSO ENCLOSED: INFORMATION DISCLOSURE STATEMENT AND REFERENCES

☐ Petition filed in prior application to extend its life to insure copendency.

☒ The Examiner's attention is directed to the prior art cited in the parent application by applicant and/or Examiner for the reasons stated therein.

☒ Please enter the attached and/or below preliminary amendment prior to calculation of filing fee:

☒ The entire disclosure of the prior application above-referenced is considered as being part of the disclosure of this new application and is hereby incorporated by reference therein.

FILING FEE IS BASED ON CLAIMS AS FILED LESS ANY HEREWITH CANCELED

Basic Filing Fee		\$	690.00
Total effective claims	20 - 20 (at least 20) = 0	x \$ 18.00	\$ 0.00
Independent claims	3 - 3 (at least 3) = 0	x \$ 78.00	\$ 0.00
If any proper multiple dependent claims now added for first time, add \$260.00 (ignore improper)			\$ 0.00
		SUBTOTAL	\$ 690.00
If "small entity," then enter half (1/2) of subtotal and subtract		-\$ (0.00)
		SECOND SUBTOTAL	\$ 690.00
Assignment Recording Fee (\$40.00)		\$	0.00
		TOTAL FEE ENCLOSED	\$ 690.00

Any future submission requiring an extension of time is hereby stated to include a petition for such time extension. The Commissioner is hereby authorized to charge any deficiency in the fee(s) filed, or asserted to be filed, or which should have been filed herewith (or with any paper hereafter filed in this application by this firm) to our **Account No. 14-1140**. A duplicate copy of this sheet is attached.

1100 North Glebe Road, 8th Floor
Arlington, Virginia 22201-4714
Telephone: (703) 816-4000
Facsimile: (703) 816-4100
RAV:eaw

NIXON & VANDERHYE P.C.
By Atty: Robert A. Vanderhye, Reg. No. 27,076

Signature: _____

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of

Brodeur et al

Atty. Ref.: **11-893**

Serial No. **To be Assigned**

Group:

Filed: **August 16, 2000**

Examiner:

For: **REINFORCED FOAM BACKED CARPET**

* * * * *

August 16, 2000

Assistant Commissioner for Patents
Washington, DC 20231

Sir:

PRELIMINARY AMENDMENT AND INFORMATION DISCLOSURE STATEMENT

Prior to the calculation of the fee in the above-identified application, please
amend the application as follows:

IN THE CLAIMS

Claim 2, line 4, delete "preformed".

Claim 5, line 1, change "4" to -2--.

Claim 6, line 1, change "2" to -1--.

Cancel claims 21 and 22 without prejudice.

REMARKS

Some cosmetic changes have been made to the claims to ensure distinctness
from the claims in the parent application.

009780" 40252960

Brodeur et al
Serial No. To be Assigned


Enclosed is a form PTO-1449 listing all of the art of record in the parent application, all of which is in the English language, and a copy of each is enclosed.

Please initial, date and return the enclosed form PTO-1449.

Early passage to issue is earnestly solicited.

Respectfully submitted,

NIXON & VANDERHYE P.C.

By: 
Robert A. Vanderhye
Reg. No. 27,076

RAV:eaw

1100 North Glebe Road, 8th Floor
Arlington, VA 22201-4714
Telephone: (703) 816-4000
Facsimile: (703) 816-4100

Our Ref.: 11-843

U.S. PATENT APPLICATION

Inventor(s): Edouard A. Brodeur, Jr.
Joseph W. Wilson

Invention: REINFORCED FOAM BACKED CARPET

***NIXON & VANDERHYTE P.C.
ATTORNEYS AT LAW
1100 NORTH GLEBE ROAD
8TH FLOOR
ARLINGTON, VIRGINIA 22201-4714
(703) 816-4000
Facsimile (703) 816-4100***

SPECIFICATION

REINFORCED FOAM BACKED CARPET

BACKGROUND AND SUMMARY OF THE INVENTION

Commercial foamed back carpet, carpet modules, and carpet tiles are commonly produced by laminating a preformed chemically blown
5 foam of the proper thickness and density to a pre-coated carpet. This is commonly done by heating the pre-coated carpet and the preformed closed cell foam to the hot melt phase of the polyvinyl chloride and pressing the two layers together. Other variations of this method, some of which involve adhesives, are common. Most of these involve heating of
10 the preformed closed cell foam.

Heating of chemically blown closed cell foam always results in the expansion of the closed cells with a corresponding growth in the dimensions of this layer. In the case of tufted and back coated carpet, the thermal expansion of the solid elastomeric back coats the fibrous primary
15 backings into which the carpet yarn is tufted. The thermal expansion of this composite is much less than the expansion of the gas filled cells of the foam layer. In the case of carpet formed by implanting fibers in an elastomeric layer to which the preformed foam layer is subsequently laminated, the same differential expansion and contraction factors occur.
20 This style is referred to as Fusion Bonded Carpet. When an expanded layer is laminated in the presence of heat to another less expanded layer, tension forces develop upon cooling. These forces result in a latent tendency of the product to curl and/or dome. The foam layer wants to pull in under the product. In the case of carpet tiles, the tiles from the center
25 of the composite will dome differently from side to side.

Also in the case of carpet or tiles produced by this method, the relatively smooth under surface of the carpet or tile does not allow substrate moisture or hydrostatic pressure to dissipate, resulting in condensation of the vapors under the carpet or the tile. In addition, it is known that the stabilization of dimensions in such a product requires several reinforcing fleeces or scrims. The processes described do not lend themselves to the incorporation of several fleeces or scrims.

In the existing art, the foam layer is formed by a layer of polyvinyl chloride (PVC) plastisol (dispersion of PVC resin in plasticizer) on an impervious carrier, such as but not limited to, a stainless steel belt or a Teflon® coated wire or fiberglass belt, and expanding the layer from a density of 70 to 90 pounds per cubic foot down to 15 to 25 pounds per cubic foot. A general formulation for such a foam layer is:

		PARTS
15	PVC resin (K value 62 to 70)	100
	Plasticizer (Di Octyl Phthalate)	60 to 100
	Nitrogen producing agent (Azo Di Carbonamide)	3
	Blow promoter (Zinc Octoate)	1
	Filler (Calcium Carbonate)	0 to 150
20	Color	as needed

"K" value is a universal method of indicating the molecular weight of the PVC molecule.

After casting the formulation on the carrier belt, the PVC plastisol is heated until the material reaches 370 to 380°F, converting all the blowing agent to gaseous nitrogen.

According to the present invention the problems with curling or doming that occur in the commercial prior art are substantially eliminated, and the disadvantageous condensation of vapors under the carpet of the

tile is also substantially eliminated. The carpet tile or roll that is produced according to the present invention has a backing that is non-slip, so that if desired the carpet tiles or roll may be installed without adhesive, namely with conventional tacking of the carpet roll or tile at the perimeter portions, or utilizing like conventional techniques. The OMFRFL can also be adhered/applied using a thermoplastic material such as polypropylene, polyethylene, or other thermoplastic compound.

According to the invention, an open mesh fiber reinforced foam layer ("OMFRFL") is incorporated onto or with the back of a back coated carpet, or fusion bonded carpet. The stable construction of the finished product is the result of the addition of a scrim in the open mesh foam as well as the open nature of that layer. This fiber mesh reinforcement can be either a second or a third fiber layer. It is a third fiber layer if the open mesh scrim foam is installed after a second layer of fleece or scrim, woven or non-woven, is adhered to the back coated or fusion bonded carpet. The OMFRFL is applied either with a foamed or non-foamed adhesive system that can be solid, frothed, or latex applied and heated to cure or fuse the adhesive. The temperature needed to accomplish this (less than about 310°F) will not significantly expand the reinforced open mesh foam across the width or in the lengthwise direction of the product any more than the carpet to which it is being bonded. The OMFRFL can also be applied using a thermoplastic hot melt material such as amorphous polypropylene, or polyethylene that is viscous when hot and rubbery when cooled. All the expansion and subsequent contraction of the foam will be in a vertical direction to the plane of the carpet. The resulting foam backed carpet or tile allows air and hydrostatic or gas pressure to dissipate, reducing the trapped vapor's tendency to condense

under the carpet, thus conditions for mold and mildew formation are reduced.

According to one aspect of the present invention a method of producing a carpet in tile or roll form using an OMFRFL with foam nodules is provided. The method comprises the steps of: (a) Producing a carpet in tile or roll form having a primary backing through which carpet fiber bundles are tufted and a precoat locking the tufts in place to prevent easy extraction of individual fibers, so that a tufted fiber face and relatively smooth opposite back face are provided. (b) Bringing the open mesh fiber reinforced foam layer with foam nodules into intimate contact with the relatively smooth back face, And (c) substantially permanently adhering the open mesh fiber reinforced foam layer with foam nodules in contact with the relatively smooth back face to provide a carpet tile or roll that has reduced curling or doming and/or that is substantially prevented from curling or doming and may be installed with or without adhesive.

There are two alternative manners in which the method steps (b) and (c) may be carried out. According to one aspect of the method, a preformed back or precoated carpet has a non-fused adhesive system associated therewith, onto which the OMFRFL is formed, with subsequent fusing; or according to another aspect, while the vinyl backing of the carpet roll or tile still has hot melt properties as it emerges from the final fusion oven, the OMFRFL is forced into intimate contact therewith.

That is, according to the first aspect of the method of the invention, step (c) is practiced by applying a non-fused adhesive formulation to the relatively smooth back face, and then after step (b), fusing the adhesive at a temperature low enough (e.g. a maximum fusing temperature of 310°F, preferably a maximum temperature of about 300°F) to prevent the collapse of the preformed foam nodules of the open

009780 2055953

mesh fiber reinforced foam layer. Step (c) is further practiced by applying as the adhesive formulation a formulation comprising, or consisting essentially of:

	PVC Copolymer	100 parts
5	Plasticizer	50-100 parts
	Filler	0-200 parts
	Silicone surfactant	0-4 parts
	Fumed silica	0-2 parts.

Preferably step (c) is further practiced by applying as the adhesive
10 formulation about 25-150 parts filler, sufficient silicone surfactant to provide a formulation density below 50 pounds per cubic foot, and sufficient fumed silica to provide a formulation Brookfield viscosity of about 30,000 - 60,000 centipoise at a spindle speed of 2 rpm.

In practice of the second aspect of the method of the invention,
15 step (c) is practiced by practicing step (a) using a fusion oven, and so that the relatively smooth carpet back face has hot melt properties as it emerges from the fusion oven; and step (b) is practiced by forcing the open mesh fiber reinforced foam layer with foam nodules into intimate contact with the relatively smooth back face so that the back face
20 contacts, or at least partially envelops, the foam nodules to provide a substantially instant bond. Step (c) may be further practiced by providing as at least part of the carpet back, contacting the OMFRFL, a formulation comprising (or consisting essentially of):

	PVC resin with a K value of 62-75	100 parts
25	Plasticizer	60-100 parts
	Filler	0-250 parts,

and substantially devoid of blowing agent (preferably having no more than trace amounts). There is also the further step of cooling the carpet with

OMFRFL with foam nodules backing, which cooling takes place during normal processing.

In both aspects of the method of the invention, step (a) may be further practiced to provide a reinforcing scrim (as is conventional for carpet tiles) as part of the carpet adjacent the relatively smooth back face, the scrim typically being a fleece, woven, or non-woven in construction as is conventional. Also, in both aspects of the method, step (b) may be practiced utilizing rollers which engage the tufted face of the carpet roll or tile, and the face of the OMFRFL opposite the carpet tile or roll, and squeezing them together with pressure that is adjusted depending upon the details of the materials used so that the appropriate intimate contact is reached without squeezing necessary somewhat fluid materials out of the nip area of the rollers. Other conventional equipment aside from the rollers may also be used for this purpose, including converging conveyor belts, relatively low friction surfaces, combinations thereof, or the like.

According to another aspect of the present invention a carpet roll or tile is provided comprising the following components: A primary backing having carpet fiber bundles tufted therethrough, the fibers bundles providing a tufted face. A precoat locking the tufts in place to prevent easy extraction of individual fibers and providing a relatively smooth back face opposite the tufted face. And an open mesh fiber reinforced foam layer with foam nodules held in substantially intimate contact with the relatively smooth back face.

The OMFRFL with foam nodules is preferably held in substantially intimate contact with the relatively smooth back face by a fused adhesive, such as an adhesive having a formulation comprising or consisting essentially of:

PVC Copolymer	100 parts
Plasticizer	50-100 parts
Filler	0-200 parts

a sufficient amount of silicone surfactant to provide a formulation

5 density below 50 pounds per cubic foot, and

a sufficient amount of fumed silica to provide a formulation
pre-fusing Brookfield viscosity of about 30,000 - 60,000 centipoise at a
spindle speed of 2 rpm.

Alternatively, the OMFRFL with foam nodules may be held in
10 substantially intimate contact with the relatively smooth back face by a hot
melt formulation of the back face comprising or consisting essentially of:

PVC resin with a K value of 62-75	100 parts
Plasticizer	60-100 parts
Filler	0-250 parts,

15 and substantially devoid of blowing agent. The hot melt formulation is not
limited to PVC, but can also be any thermoplastic material that acts as a
flexible layer or adhesive.

The hot melt formulation is not limited to PVC but can also be any
thermoplastic material that acts as a flexible layer or adhesive.

20 According to another aspect of the present invention a carpet tile is
provided. The carpet tile is substantially the same as the carpet roll as
described above, except that it additionally includes a reinforcing scrim
adjacent the relatively smooth back face and held in place at least in part
by the precoat. Under some circumstances the carpet roll may also have
25 a reinforcing scrim. Also, according to the invention carpet rolls or tiles
may be made by practicing the method steps described above with
respect to the method aspect of the invention.

It is a primary object of the present invention to provide a carpet in tile or roll form having at least some of the following advantages; it is substantially prevented from curling or doming, has enhanced antagonistic conditions to mold and mildew formation, and may even be installed without adhesive if desired. This and other objects of the invention will become clear from an inspection of the detailed description of the invention, and from the appended claims.

BRIEF DESCRIPTION OF THE DRAWINGS

FIGURE 1 is a side cross sectional schematic view of an exemplary carpet tile or roll according to the invention, which includes a reinforcing scrim;

FIGURE 2 is a bottom perspective view of an exemplary carpet tile or roll according to the present invention with a portion of the open mesh fiber reinforced layer peeled away for clarity of illustration, and without the reinforcing scrim of the FIGURE 1 embodiment;

FIGURES 3 through 5 are top schematic plan views of alternative configurations of open mesh reinforced fiber foam layers with foam nodules that may be utilized with the carpet roll or tile of FIGURES 1 or 2, according to the invention;

FIGURE 6 is a diagrammatic view showing basic method steps that may be practiced according to one aspect of the method of the present invention; and

FIGURE 7 is like FIGURE 6 only for a second embodiment of an exemplary method according to the present invention.

00939307-001000

DETAILED DESCRIPTION OF THE DRAWINGS

FIGURE 1 schematically illustrates in cross section an exemplary carpet according to the invention. The carpet 10 illustrated in FIGURE 1 may either be in tile (module) or roll form, although the particular version illustrated in FIGURE 1 is more commonly in tile form. It includes a primary backing 11 of conventional construction, such as a woven or non-woven fabric composed of natural or synthetic fibers or combinations thereof, commonly used such fibers being jute, polypropylene, polyester, and nylon, with or without some glass fibers. Tufted through the primary backing 11 are the carpet fiber bundles 12 which are typically in a closed loop configuration or in a cut pile configuration, as illustrated in FIGURE 1 which shows the bottom portion of the cut pile at 13 beneath the primary backing 11, and an open configuration on the opposite side of the primary backing 11, defining a cut pile tufted face 14. The fibers of the fiber bundles 12 may be of any conventional construction used for carpets, such as nylon, polyester, acrylic, olefins such as polyethylene, or polypropylene, or natural fibers such as cotton or wool.

Locking the tufts 12 in place is a layer of material 15 which is often referred to in the trade as a precoat or first back coat. The precoat 15 is typically an elastomeric or bituminous layer which saturates the loops 13 of the fiber bundles 12 to prevent easy extraction of the individual fiber or the bundles 12 from the carpet 10.

In the embodiment illustrated in FIGURE 1, the carpet 10 also includes a reinforcing scrim 16, such as a lightweight fiberglass fleece, or some other woven or non-woven scrim, which is provided for dimensional stability. While the scrim 16 may be used with carpets in roll

configuration, it is particularly desirable for carpet tiles and like carpet modules.

According to the present invention, on the opposite side of the precoat 15 on the primary backing 11 is an open mesh fiber reinforced foam layer ("OMFRFL") with foam nodules, illustrated generally at 17 in FIGURE 1, which is held in place utilizing a holding system shown only schematically at 18 in FIGURE 1. The OMFRFL is adhered to the back face 19, which, in contrast to the tufted face 14, is relatively smooth, and opposite the tufted face 14. Though the back face 19 is relatively smooth (compared to the tufted face 14), it preferably does have surface texturing rather than being completely macroscopically smooth (such as are conventional wood, ceramic, or metal surfaces).

The OMFRFL 17, as seen in both FIGURES 1 and 2, includes foam nodules 20 with openings 21 between the nodules 20. The OMFRFL is a commercially available known construction, which has a plurality of foam shapes of various thicknesses, densities, patterns, or the like and is typically formed by immersing a foam scrim formed of natural or synthetic fibers which are either knitted or woven into a network having intermittent openings spaced along the surface thereof in a repeating pattern. A typical weight is about .5-2.5 oz/square foot.

The openings 21 may be randomly spaced and may be rectangular, or have other polygonal shapes, or even circular shapes, or combinations of such shapes. Typically the scrim forming the OMFRFL 17 is dipped in a liquid thermoplastic material such as PVC, excess PVC is removed to leave a combination of heavy and light coatings, and then the structure is cured in an oven. This provides either an orderly or random network of thick and thin areas. In the preferred embodiment gas is released during the curing cycle providing thick and thin areas of foam

proportional to the amount of the liquid PVC that is held onto the strands of fibers or trapped in the knotted areas of the scrim construction. One conventional product that may be utilized as the structure 17 according to the present invention is sold by Vantage Industries of Atlanta, Georgia, under the trademarks "Rugsaver" and "Sultan". Various configurations of the structure 17 per se are shown in PCT/US96/20448.

FIGURE 2 illustrates a carpet tile or roll 10' according to the invention which is substantially the same as the construction 10 in FIGURE 1 except that no reinforcing scrim 16 is provided. The element 18 schematically illustrated in FIGURES 1 and 2 may comprise a non-fused adhesive formulation which is subsequently fused in such a manner as to not collapse the preformed foam nodules 20 of the OMFRFL 17, or may be all or part of the precoat 15.

FIGURES 3 through 5 illustrate various other forms that the OMFRFL may take according to the invention. For example, the structure 117 in FIGURE 3 includes the foam nodules 120 and the openings (rectangular) 121 between them, and also contains other, non-nodule, material 22 between the nodules 120.

FIGURE 4 shows a OMFRFL 217 having nodules 220 and openings 221 with generally fiber-like non-nodule elements 23 interconnecting the nodules 220.

FIGURE 5 shows another OMFRFL 317 having nodules 320 and defining openings 321, in this case the openings 321 being small, and there being a number of small nodules 24 between the major nodules 320 helping to define the openings 321. All of the constructions 117, 217, 317 are known per se from PCT/US96/20448, and other variations thereof may also be provided.

FIGURE 6 schematically illustrates the basic steps in the practice of one aspect of the method according to the present invention. A back coated carpet, or fusion bonded carpet, is produced using conventional techniques and then, as indicated schematically at 26 in FIGURE 6, a thermoplastic adhesive layer is applied to the carpet back face 19. The thermoplastic adhesive may be applied in any suitable conventional manner, such as by coating, spraying, or application to the OMFRFL which then comes into contact with the backing 19. At stage 26 the adhesive (schematically illustrated at 18 in FIGURES 1 and 2) is a non-fused adhesive formulation. The formulation that is preferred comprises or consists essentially of:

	PARTS
Copolymer PVC	100
Plasticizer	50 to 100
15 Filler [e.g. Calcium Carbonate]	0 to 200
Silicone surfactant	0 to 4
Fumed Silica	0 to 2.

The preferred choice for a PVC resin for this application is a copolymer with preferably about 4 to 5% acetate to minimize the requirement for additional heat above what would be required to fuse the adhesive below 300 to 310°F. Excessive time and heat will collapse the preformed foam.

The fumed silica [e.g. 1-2 parts] is used as needed to produce a viscosity with a high degree of pseudoplasticity as exemplified by a Brookfield viscosity value of 30,000 to 60,000 centipoise at a spindle speed of 2 RPM's [e.g. 1-2 parts].

The plasticizer may be di octyl phthalate (DOP) or another of the many functional plasticizers used in this trade, including but not limited to

di hexyl phthalate, butyl benzyl phthalate, plasticizers based on adipic acid, terephthalic acid, sebacates; azelates, and phosphates.

A silicone surfactant (e.g. Dow Corning 1250, 1-3 parts) is used to reduce the density of the adhesive layer by mechanically frothing the plastisol to densities below 50 pounds per cubic foot.

While calcium carbonate is a preferred filler, there are literally dozens of available fillers that can be used effectively. Typically about 25-150 parts filler are utilized.

The next step of this aspect of the method, illustrated schematically at 27 in FIGURE 6, comprises forcing the OMFRFL into the non-fused carpet adhesive layer 18. Step 27 may be accomplished utilizing a pair of rollers forming a nip with one roller engaging the tufted face 14 and the other the nodules 20 of the OMFRFL 17 on the opposite face thereof from the tufted face 14, the rollers applying appropriate pressure to move the OMFRFL 17 into intimate contact with the non-fused thermoplastic, adhesive system 18 while not squeezing out any fluidic materials between the nip. Alternatively, conventional belts, low friction surfaces, or combinations thereof with each other and with rollers, or like conventional structures, may be utilized.

After step 27, as illustrated schematically at 28 in FIGURE 6, the adhesive layer 18 is fused without collapsing the foam nodules 20 by applying a temperature significantly lower than the temperature that would collapse the nodules 20. Typically, the maximum fusing temperature at 28 is about 310°F, or about 300°F. Fusing is accomplished by using a conventional fusion oven or the like.

The product produced according to the present invention is a stabilized carpet tile or roll as indicated generally by block 29 in FIGURE 6, an exemplary tile being shown schematically at 30 in FIGURE 6, and

an exemplary roll shown schematically at 31. The structures 30, 31 are substantially prevented from curling or doming by the structure 17, the antagonistic conditions for the formation of mold and mildew are enhanced, and the structure provides such firm non-stick characteristics that, if desired, tile 30 or roll 31 may be installed without adhesive, as indicated schematically at 32 in FIGURE 6. Conventional perimeter installation would still be utilized.

FIGURE 7 illustrates an alternative method of producing a carpet tile or roll according to the invention. As indicated at box 36 in FIGURE 7, the carpet tile or roll is produced with a hot melt backing formulation. A typical formulation that may be used for this purpose, which comprises completely the precoat 15 or the outwardmost facing portion of the precoat 15, may comprise or consist of:

	PVC resin, with a K value 62 to 75	100
15	Plasticizer (e.g. DOP)	60 to 100
	Filler (e.g. Calcium Carbonate)	0 to 250.

Preferably there is substantially no blowing agent. The extent of penetration of the OMFRFL into the backing is determined by regulating the hot melt properties by a higher or lower K value of the resin. A K value below 65 will produce an extremely soft layer, while K values above 75 will result in a dry film.

As indicated at 37 in FIGURE 7, the next step in this aspect of the method is to force the OMFRFL into the still fluid hot melt backing, the forcing being accomplished in the same way as described above with respect to step 28. This forcing action must take place substantially immediately upon emergence of the carpet tile or roll from the final fusion oven so that the hot melt formulation described above still has fluid properties. If desired, and if no scrim 16 is provided, the OMFRFL 17

may be forced so that it actually comes into contact with at least some of the bottom loops 13 of the tufted fiber bundles 14.

After step 38 the carpet 10 or 10' is cooled as indicated at 38 in FIGURE 7. Cooling typically can be accomplished merely by normal
5 exposure to the air so that the fluid properties of the hot melt backing (such as the backing portion 18 illustrated in FIGURES 1 and 2) are lost, and the material of the backing solidifies around and envelops and forms an envelope or amalgam with the material of the OMFRFL 17, such as being provided in the openings 21 and engaging a significant portion of
10 the nodules 20. A conventional forced cooling apparatus could also be used. The boxes 29 and 32 in FIGURE 7 are the same as in FIGURE 6.

In both the method aspects of FIGURES 6 and 7 according to the invention, a conventional scrim 16 may be provided as part of the carpet adjacent the relatively smooth back face 19.

15 It will thus be seen that according to the present invention a highly advantageous carpet in tile or roll form, and a method of production thereof, have been provided. While the invention has been herein shown and described in what is presently conceived to be the most practical and preferred embodiment thereof, it will be apparent to those of ordinary skill
20 in the art that many modifications may be made thereof within the scope of the invention which scope is to be accorded the broadest interpretation of the appended claims so as to encompass all equivalent structures and methods.

WHAT IS CLAIMED IS:

1 1. A method of producing a carpet in tile or roll form using an open
2 mesh fiber reinforced foam layer with foam nodules comprising the steps
3 of:

4 (a) producing a carpet in tile or roll form having a primary backing
5 through which carpet fiber bundles are tufted and a precoat locking the
6 tufts in place to prevent easy extraction of individual fibers, so that a
7 tufted fiber face and relatively smooth opposite back face are provided;

8 (b) bringing the open mesh fiber reinforced foam layer with foam
9 nodules into intimate contact with the relatively smooth back face; and

10 (c) adhering the open mesh fiber reinforced foam layer with foam
11 nodules in contact with the relatively smooth back face to provide a carpet
12 tile or roll that is substantially prevented from curling or doming, or curling
13 or doming is significantly reduced, and may be installed without adhesive
14 if desired.

1 2. A method as recited in claim 1 wherein step (c) is practiced by
2 applying a non-fused adhesive formulation to the relatively smooth back
3 face, and then after step (b); fusing the adhesive at a temperature low
4 enough to prevent the collapse of the preformed foam nodules of the
5 open mesh fiber reinforced foam layer.

1 3. A method as recited in claim 2 wherein step (c) is practiced by
2 exposing the adhesive with attached open mesh fiber reinforced foam
3 layer with foam nodules to a maximum fusing temperature of about
4 310°F.

009780-2055950

1 4. A method as recited in claim 3 wherein step (c) is further
2 practiced by applying as the adhesive formulation a formulation
3 comprising:

4	PVC Copolymer	100 parts
5	Plasticizer	50-100 parts
6	Filler	0-200 parts
7	Silicone surfactant	0-4 parts
8	Fumed silica	0-2 parts.

1 5. A method as recited in claim 4 wherein step (c) is further
2 practiced by applying as the adhesive formulation about 25-150 parts
3 filler, sufficient silicone surfactant to provide a formulation density below
4 50 pounds per cubic foot, and sufficient fumed silica to provide a
5 formulation Brookfield viscosity of about 30,000 - 60,000 centipoise at a
6 spindle speed of 2 rpm.

1 6. A method as recited in claim 2 wherein step (c) is further
2 practiced by applying a formulation consisting essentially of PVC
3 copolymer, plasticizer, filler, silicone surfactant, and fumed silica.

1 7. A method as recited in claim 1 wherein step (c) is practiced by
2 practicing step (a) using a fusion oven, and so that the relatively smooth
3 face of the backing has fluid properties as it emerges from the fusion
4 oven; and wherein step (b) is practiced by forcing the open mesh fiber
5 reinforced foam layer with foam nodules into intimate contact with the still
6 fluid portion of relatively smooth back face so that the hot melt backing at

009730-2066960

7 least partially envelops the foam nodules to provide a substantially instant
8 bond.

1 8. A method as recited in claim 7 wherein step (c) is further
2 practiced by providing as at least part of the carpet back a formulation
3 comprising:

4	PVC resin with a K value of 62-75	100 parts
5	Plasticizer	60-100 parts
6	Filler	0-250 parts,

7 and substantially devoid of blowing agent.

1 9. A method as recited in claim 7 wherein step (c) is further
2 practiced by providing as part of the carpet back face PVC resin having a
3 K value between 62-75, and substantially devoid of blowing agent.

1 10. A method as recited in claim 7 comprising the further step of
2 cooling the carpet with open mesh fiber reinforced foam layer with foam
3 nodules backing.

1 11. A method as recited in claim 2 wherein step (a) is further
2 practiced to provide a reinforcing scrim as part of the carpet adjacent the
3 relatively smooth back face.

1 12. A method as recited in claim 7 wherein step (a) is further
2 practiced to provide a reinforcing scrim as part of the carpet adjacent the
3 relatively smooth back face.

00959307-001000

1 13. A carpet tile comprising:
 2 a primary backing having carpet fiber bundles tufted therethrough,
 3 the fibers bundles providing a tufted face;
 4 a precoat locking the tufts in place to prevent easy extraction of
 5 individual fibers and providing a relatively smooth back face opposite the
 6 tufted face;
 7 a reinforcing scrim adjacent the relatively smooth back face and
 8 held in place at least in part by said precoat; and
 9 an open mesh fiber reinforced foam layer with foam nodules held
 10 in substantially intimate contact with the relatively smooth back face.

1 14. A carpet tile as recited in claim 13 wherein said open mesh
 2 fiber reinforced foam layer with foam nodules is held in substantially
 3 intimate contact with the relatively smooth back face by a fused adhesive.

1 15. A carpet tile as recited in claim 14 wherein said fused
 2 adhesive comprises a formulation comprising:
 3 PVC Copolymer 100 parts
 4 Plasticizer 50-100 parts
 5 Filler 0-200 parts
 6 a sufficient amount of silicone surfactant to provide a formulation
 7 density below 50 pounds per cubic foot, and
 8 a sufficient amount of fumed silica to provide a formulation
 9 pre-fusing Brookfield viscosity of about 30,000 - 60,000 centipoise at a
 10 spindle speed of 2 rpm.

1 16. A carpet tile as recited in claim 13 wherein said open mesh
2 fiber reinforced foam layer with foam nodules is held in substantially
3 intimate contact with the relatively smooth back face by a formulation of
4 said back face comprising:

5	PVC resin with a K value of 62-75	100 parts
6	Plasticizer	60-100 parts
7	Filler	0-250 parts,

8 and substantially devoid of blowing agent.

1 17. A carpet roll comprising:

2 a primary backing having carpet fiber bundles tufted therethrough,
3 the fibers bundles providing a tufted face;

4 a precoat locking the tufts in place to prevent easy extraction of
5 individual fibers and providing a relatively smooth back face opposite the
6 tufted face; and

7 an open mesh fiber reinforced foam layer with foam nodules held
8 in substantially intimate contact with the relatively smooth back face.

1 18. A carpet roll as recited in claim 17 wherein said open mesh
2 fiber reinforced foam layer with foam nodules is held in substantially
3 intimate contact with the relatively smooth back face by a fused adhesive.

1 19. A carpet roll as recited in claim 18 wherein said fused
2 adhesive comprises a formulation comprising:

3	PVC Copolymer	100 parts
4	Plasticizer	50-100 parts
5	Filler	0-200 parts

6 a sufficient amount of silicone surfactant to provide a formulation
 7 density below 50 pounds per cubic foot, and
 8 a sufficient amount of fumed silica to provide a formulation
 9 pre-fusing Brookfield viscosity of about 30,000 - 60,000 centipoise at a
 10 spindle speed of 2 rpm.

1 20. A carpet roll as recited in claim 17 wherein said open mesh
 2 fiber reinforced foam layer with foam nodules is held in substantially
 3 intimate contact with the relatively smooth back face by a formulation of
 4 said back face comprising:

5	PVC resin with a K value of 62-75	100 parts
6	Plasticizer	60-100 parts
7	Filler	0-250 parts,
8	and substantially devoid of blowing agent.	

1 21. A carpet tile or roll made by practicing steps (a)-(c) of claim 4.

1 22. A carpet tile or roll made by practicing steps (a)-(c) of claim 7.

ABSTRACT OF THE DISCLOSURE

A carpet in tile or roll form is produced using an open mesh reinforced foam layer with foam nodules. The carpet is produced having a primary backing through which carpet fiber bundles are tufted and a precoat layer which locks the tufts in place to prevent easy extraction of the fibers so that a tufted face and a relatively smooth back face are provided. The foam layer with foam nodules is brought into intimate contact with the relatively smooth back face, and is substantially permanently adhered to it producing a carpet tile or roll that is substantially prevented from curling or doming (or they are significantly reduced) and may be installed without adhesive if desired. Adhering may be practiced by using a non-fused adhesive formulation which is subsequently fused at a low temperature (about 310°F or less), or by forcing the foam layer with foam nodules into contact with the carpet back while the hot melt backing is still in a fluid form, or by use of a thermoplastic layer between the carpet and foam sheet.

Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6





Fig. 7



RULE 63 (37 C.F.R. 1.63)
DECLARATION AND POWER OF ATTORNEY
FOR PATENT APPLICATION
IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

As a below named inventor, I hereby declare that my residence, post office address and citizenship are as stated below next to my name, and I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

REINFORCED FOAM BACKED CARPET

the specification of which (check applicable box(es)):

☒ is attached hereto
☐ was filed on _____ as U.S. Application Serial No. _____ (Atty Dkt. No. 11-843)
☐ was filed as PCT International application No. _____ on _____
 and (if applicable to U.S. or PCT application) No. was amended on _____

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above. I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with 37 C.F.R. 1.56. I hereby claim foreign priority benefits under 35 U.S.C. 119/365 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed or, if no priority is claimed, before the filing date of this application:

Priority Foreign Application(s):

Application Number	Country	Day/Month/Year Filed
--------------------	---------	----------------------

I hereby claim the benefit under 35 U.S.C. §119(e) of any United States provisional application(s) listed below.


Application Number	Date/Month/Year Filed
--------------------	-----------------------

I hereby claim the benefit under 35 U.S.C. 120/365 of all prior United States and PCT international applications listed above or below and, insofar as the subject matter of each of the claims of this application is not disclosed in such prior applications in the manner provided by the first paragraph of 35 U.S.C. 112, I acknowledge the duty to disclose material information as defined in 37 C.F.R. 1.56 which occurred between the filing date of the prior applications and the national or PCT international filing date of this application:

Prior U.S./PCT Application(s):

Application Serial No.	Day/Month/Year Filed	Status: patented pending, abandoned
------------------------	----------------------	--

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon. And I hereby appoint NIXON & VANDERHYE P.C., 1100 North Glebe Rd., 8th Floor, Arlington, VA 22201-4714, telephone number (703) 816-4000 (to whom all communications are to be directed), and the following attorneys thereof (of the same address) individually and collectively my attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith and with the resulting patent: Arthur R. Crawford, 25327; Larry S. Nixon, 25640; Robert A. Vanderhye, 27076; James T. Hosmer, 30184; Robert W. Farns, 31352; Richard G. Besha, 22770; Mark E. Nusbaum, 32348; Michael J. Keenan, 32106; Bryan H. Davidson, 30251; Stanley C. Spooner, 27393; Leonard C. Mitchard, 29009; Duane M. Byers, 33363; Jeffrey H. Nelson, 30481; John R. Lastova, 33149; H. Warren Burnam, Jr. 29366; Thomas E. Byrne, 32205; Mary J. Wilson, 32955; J. Scott Davidson, 33489; Alan M. Kagen, 36178; William J. Griffin, 31260; Robert A. Moian, 29834; B. J. Sadoff, 36663; James D. Berquist, 34776; Updeep S. Gill, 37334.

1.	Inventor's Signature: 	Date: 4/13/98
	Inventor: Edouard A. Brodeur, Jr. (first) MI (last)	U.S.A. (citizenship)
	Residence: (city) Marietta (state/country) Georgia	
	Post Office Address: 141 Huntcliff Court, Marietta, Georgia (Zip Code) 30066	
2.	Inventor's Signature: _____	Date: _____
	Inventor: Joseph W. Wilson (first) MI (last)	U.S.A. (citizenship)
	Residence: (city) Buena Vista (state/country) Virginia	
	Post Office Address: 1473 Forest Avenue, Buena Vista, Virginia (Zip Code) 24416	
3.	Inventor's Signature: _____	Date: _____
	Inventor: _____ (first) MI (last)	(citizenship)
	Residence: (city) _____ (state/country) _____	
	Post Office Address: _____ (Zip Code) _____	

FOR ADDITIONAL INVENTORS, check box ☐ and attach sheet with same information and signature and date for each.

RULE 63 (37 C.F.R. 1.63)
DECLARATION AND POWER OF ATTORNEY
FOR PATENT APPLICATION
IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

As a below named inventor, I hereby declare that my residence, post office address and citizenship are as stated below next to my name, and I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

REINFORCED FOAM BACKED CARPET

the specification of which (check applicable box(es)):

- ☒ is attached hereto
☐ was filed on _____ as U.S. Application Serial No. _____ (Atty Dkt. No. 11-843)
☐ was filed as PCT International application No. _____ on _____
and (if applicable to U.S. or PCT application) No. was amended on _____

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above. I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with 37 C.F.R. 1.56. I hereby claim foreign priority benefits under 35 U.S.C. 119/365 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed or, if no priority is claimed, before the filing date of this application:

Priority Foreign Application(s):

Application Number	Country	Day/Month/Year Filed

I hereby claim the benefit under 35 U.S.C. §119(e) of any United States provisional application(s) listed below.

Application Number	Date/Month/Year Filed

I hereby claim the benefit under 35 U.S.C. 120/365 of all prior United States and PCT international applications listed above or below and, insofar as the subject matter of each of the claims of this application is not disclosed in such prior applications in the manner provided by the first paragraph of 35 U.S.C. 112, I acknowledge the duty to disclose material information as defined in 37 C.F.R. 1.56 which occurred between the filing date of the prior applications and the national or PCT international filing date of this application:

Prior U.S./PCT Application(s):

Application Serial No.	Day/Month/Year Filed	Status: patented pending, abandoned

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon. And I hereby appoint NIXON & VANDERHYE P.C., 1100 North Glebe Rd., 8th Floor, Arlington, VA 22201-4714, telephone number (703) 816-4000 (to whom all communications are to be directed), and the following attorneys thereof (of the same address) individually and collectively my attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith and with the resulting patent: Arthur R. Crawford, 25327; Larry S. Nixon, 25640; Robert A. Vanderhye, 27076; James T. Hosmer, 30184; Robert W. Faris, 31352; Richard G. Besha, 22770; Mark E. Nusbaum, 32348; Michael J. Keenan, 32106; Bryan H. Davidson, 30251; Stanley C. Spooner, 27393; Leonard C. Mitchard, 29009; Duane M. Byers, 33363; Jeffrey H. Nelson, 30481; John R. Lastova, 33149; H. Warren Burnam, Jr. 29366; Thomas E. Byrne, 32205; Mary J. Wilson, 32955; J. Scott Davidson, 33489; Alan M. Kagen, 36178; William J. Griffin, 31260; Robert A. Molan, 29834; B. J. Sadoff, 36663; James D. Berquist, 34776; Updeep S. Gill, 37334.*

- | | | | |
|----|------------------------------------|---|--|
| 1. | Inventor's Signature:
Inventor: | <div style="display: flex; justify-content: space-between;"> <div> <u>Edouard</u>
(first)
<u>Marietta</u>
Residence (city)
<u>141 Huntcliff Court, Marietta, Georgia</u>
Post Office Address
(Zip Code) <u>30066</u> </div> <div> <u>A.</u>
MI
<u>Georgia</u>
(state/country) </div> <div> <u>Brodeur, Jr.</u>
(last) </div> </div> | Date: _____
<u>U.S.A.</u>
(citizenship) |
| 2. | Inventor's Signature:
Inventor: | <div style="display: flex; justify-content: space-between;"> <div> <u>Joseph</u>
(first)
<u>Buena Vista</u>
Residence (city)
<u>1473 Forest Avenue, Buena Vista, Virginia</u>
Post Office Address
(Zip Code) <u>24416</u> </div> <div> <u>W.</u>
MI
<u>Virginia</u>
(state/country) </div> <div> <u>Wilson</u>
(last) </div> </div> | Date: <u>3-30-98</u>
<u>U.S.A.</u>
(citizenship) |
| 3. | Inventor's Signature:
Inventor: | <div style="display: flex; justify-content: space-between;"> <div>
(first)

Residence (city)
Post Office Address
(Zip Code) </div> <div>
MI

(state/country) </div> <div>
(last) </div> </div> | Date: _____

(citizenship) |

FOR ADDITIONAL INVENTORS, check box ☐ and attach sheet with same information and signature and date for each.